
DCG12-26

Gel VRLA
DCG Series - Deep Cycle Gel



Maintenance-free gel batteries with a thixotropic electrolyte deliver excellent deep-cycle endurance, enhanced safety, and strong vibration resistance. Built for harsh and higher temperature environments, they provide reliable cycling performance in applications such as medical devices, mobility equipment, and renewable energy systems.

Performance Specs


Nominal Voltage	12.0 Volts, (6.0 cells)
Nominal Capacity	
20-hr. (1.22A to 10.5 Volts)	24.4Ah
10-hr. (2.23A to 10.5 Volts)	22.3Ah
5-hr. (3.96A to 10.2 Volts)	19.8Ah
1-hr. (14.0A to 9.6 Volts)	14.0Ah
Approximate Weight	18.74lbs, (8.5kg)
Dimensions +/- 0.08 in. (+/- 2mm) for length, width, and height dimensions	**L:** 6.54in, 166.0mm **W:** 6.89in, 175.0mm **H:** 4.92in, 125.0mm **TH:** 4.92in, 125.0mm
Internal Resistance (approx.) mΩ	20.0mΩ
Max Short Circuit Discharge Current	600.0A
Operating Temperature Range	
Charge	–4°F (–20°C) to 104°F (40°C)
Discharge	–4°F (–20°C) to 140°F (60°C)
Case	ABS (UL94 HB or V-0 optional)
Recommended Power-Sonic Charger	PSC-122000ACX

Configuration Options

- DCG12-26 M5

Available Terminals (mm)


T15: Threaded insert with 5mm stud fastener




To ensure safe and efficient operation always refer to the latest edition of our Technical Manual, as published on our website. © 2026. Power-Sonic Corporation. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.

Graphs


Capacity Retention SLA




PDC Cycle Life



SLA Charging



SLA Discharge Rates



Constant Current

VoltageOverTime	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.60V/cell	31.8	23.3	17.1	14.0	10.3	8.38	6.22	4.97	4.17	3.56	2.79	2.36	1.27
1.65V/cell	29.6	22.0	16.0	13.3	9.85	8.13	6.03	4.83	4.08	3.5	2.76	2.33	1.26
1.67V/cell	29.3	21.8	15.9	13.2	9.77	8.05	5.98	4.79	4.04	3.47	2.74	2.31	1.25
1.70V/cell	28.2	21.0	15.4	12.7	9.47	7.85	5.8	4.67	3.96	3.42	2.7	2.28	1.24
1.75V/cell	26.1	19.6	14.5	12.0	8.93	7.4	5.57	4.52	3.84	3.3	2.62	2.23	1.22
1.80V/cell	23.3	17.8	13.4	11.2	8.39	6.98	5.27	4.32	3.7	3.19	2.54	2.19	1.2
1.85V/cell	20.3	15.9	12.2	10.2	7.71	6.46	4.92	4.07	3.52	3.04	2.42	2.1	1.15

Constant Power


VoltageOverTime	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.60V/cell	57.4	42.9	32.0	26.6	19.5	16.0	12.0	9.6	8.1	6.94	5.49	4.67	2.52
1.65V/cell	54.0	40.8	30.3	25.3	18.8	15.6	11.7	9.39	7.91	6.82	5.43	4.6	2.5
1.67V/cell	53.5	40.4	30.0	25.1	18.7	15.5	11.6	9.3	7.88	6.8	5.41	4.58	2.49
1.70V/cell	52.0	39.3	29.2	24.4	18.2	15.1	11.3	9.1	7.74	6.71	5.34	4.54	2.47
1.75V/cell	48.8	37.0	27.7	23.2	17.3	14.4	10.8	8.8	7.53	6.5	5.19	4.44	2.44
1.80V/cell	43.9	34.0	25.8	21.8	16.3	13.6	10.3	8.5	7.27	6.29	5.04	4.36	2.39
1.85V/cell	38.9	30.7	23.6	19.8	15.0	12.6	9.64	8.0	6.95	6.01	4.82	4.18	2.3

To ensure safe and efficient operation always refer to the latest edition of our Technical Manual, as published on our website. © 2026. Power-Sonic Corporation. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.

Charging

Cycle Applications: Apply constant voltage charge at 2.35VPC – 2.45VPC (14.1 to 14.7 volts for 12V Monobloc) at 20°C. The initial charging current should be set at less than C/5 Amps. Switch to float charge when the current falls to a 3% capacity rate to avoid overcharging. Stand-By or "Float" Service: Apply constant voltage charge of 2.25VPC – 2.30VPC (13.5 to 13.8 volts for 12V Monobloc) at 20°C. When held at this voltage, the battery will seek its own current level and maintain itself in a fully charged condition. Temperature Compensation: Charging voltage for both cyclic and stand-by applications should be regulated in relation to ambient temperature. As temperature rises, charging voltage should be reduced to prevent overcharge and increased as the temperature falls to avoid undercharge. For further charging information, including temperature compensation factors, see the Power-Sonic Technical Manual.

Engineering Drawing



For Further Information

Please refer to our website, **www.power-sonic.com**, for a complete range of useful downloads, such as product catalogs, material safety data sheets (MSDS), ISO certification, etc.

Approvals

ISO 9001:2015 certification ensures consistent quality management and manufacturing standards for energy storage products.

California Proposition 65 compliant, providing consumer safety through reduced chemical exposure in battery manufacturing.

Sealed lead-acid batteries classified UN2800 non-spillable, certified safe for air, sea, and ground transport worldwide.

UL Recognized mark certifies safety-tested components for electrical reliability in battery and energy storage systems.

To ensure safe and efficient operation always refer to the latest edition of our Technical Manual, as published on our website. © 2026. Power-Sonic Corporation. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.

Updated 8/18/2026 4:34 PM **Version 1.2**